
MOTORCYCLE BATTERY







Terminal Dimensions: (in./mm)








Physical Dimensions: (in./mm)







Length:5.91in(150mm) Width:3.43in(87mm) Height:5.20in(132mm)

Tolerances are ± 0.04 inches (± 1 mm) and ± 0.08 inches (± 2 mm) for height.

Features

- Advanced sulfate-resistant technology.
- Advanced calcium lead alloy technology.
- Maintenance-free design.
- Factory activated, Ready to install and go!
- Absorbed Glass Mat (AGM) technology.


Performance Specifications

Nominal Voltage 12 vo				
Nominal Capacity 25 ℃ (77°F)				
20-hr.	(0.6A to 10.5 volts)	12.96AH		
10-hr.	(1.2A to 10.5 volts)	12AH		
5-hr.	(2.4A to 10.2 volts)	9.8AH		
1C.	(12A to 9.6 volts)	5.4AH		
3C.	(36A to 9.6 volts)	4.3AH		
Approximate Weight		7.9lbs. (3.6kg)		
Cranking (by Tester)		280Amperes		
Cold Cranking (-18 °C)		160 Amperes		
Internal Resistance(at 1KHz) Approx.9.9m				
Operating Temperature Range				
Discharge		22°F(-30℃) to 122°F(50℃)		
Charge		32°F(0°C) to 104°F(40°C)		
Life Expectancy (Cycle Use)				
60% depth of discharge 250 cycle				
30% depth of discharge 400 cycl				
Shelf Life (% of normal capacity at 68°F(20°C)SOC% ocv)				
1 mon	ths	91% 12.78V		
3 months		89% 12.70V		
6 months		80% 12.5V		
Warranty	/	1 year		
Case		ABS		


MOTORCYCLE BATTERY




YTX12-BS [12V12Ah] 160A [EN]




Discharge Characteristics



Discharge Time vs. Discharge Current



Life Characteristics in Cyclic Use



Charging

Cycle Applications: Limit initial current to 0.2C. Charge until battery voltage (under charge) reaches 14.8 to 15.0 volts at 68 $\mathbb F$ (20 $\mathbb C$). Hold at 14.8 to 15.0 volts until current drops to under 50 mA. Battery is fully charged under these conditions, and charger should be disconnected or switched to "float" voltage.

Note: Due to the self-discharge characteristics of this type of battery, it is imperative that they be charged within 6 months of storage, otherwise permanent loss of capacity might occur as a result of sulfation.

Can be used to replace:

YTX12-BS		